

**PROPYPLAST SAS**

B.P.11  
 Rue de l'Industrie  
 43130 RETOURNAC  
 FRANCE  
 tel: 04 71 65 20 72  
 fax: 04 71 65 75 31  
 E-mail : [propyplast@propyplast.fr](mailto:propyplast@propyplast.fr)  
 Internet : [www.propyplast.fr](http://www.propyplast.fr)

AFTIML/12

**TECHNICAL DATA SHEET****LME W 75**

Cast film PP, printable, for "In Mould Labelling" application

Color : white

Updated : 10-20-2008

PROPERTIES	TEST METHOD	UNIT	VALUE
WEIGHT	DOCQ104	gr/m <sup>2</sup>	70.2 +/- 5%
DENSITY	DOCQ104	gr/cm <sup>3</sup>	0.937
YIELD	DOCQ104	M <sup>2</sup> /kg	14,25
DYN. COEF. OF FRICTION	DOCQ109	/	0.40
YOUNG MODULUS	DOCQ109	MPa	900
TENSILE STRENGTH	DOCQ109	MPa	SL 37 ST 25
ELONGATION	DOCQ109	%	SL 580 ST 40
CORONA TREATMENT ( after extrusion, on printable side ) only one side of LME W film is printable	DOCF002	dyn/cm	> 44

*This information is only given for general guidance and no warranty is implied.*