

**PROPYPLAST SAS**

B.P.11

Rue de l'Industrie

43130 RETOURNAC

FRANCE

tel: 04 71 65 20 72

fax: 04 71 65 75 31

E-mail : [propyplast@propyplast.fr](mailto:propyplast@propyplast.fr)Internet : [www.propyplast.fr](http://www.propyplast.fr)

FTIML/8

**TECHNICAL DATA SHEET****LMG C 100**

Cast film PP, printable, antistatic, for "In Mould Labelling" application

Color : clear

Updated : march 2008

PROPERTIES	TEST METHOD	UNIT	VALUE
WEIGHT	DOCQ104	gr/m <sup>2</sup>	90,2
YIELD	DOCQ104	M <sup>2</sup> /kg	11,09
DYN. COEF. OF FRICTION	DOCQ109	/	0.37
YOUNG MODULUS	DOCQ109	MPa	1360
TENSILE STRENGTH	DOCQ109	MPa	SL 37 ST 30
ELONGATION	DOCQ109	%	SL 580 ST 370
CORONA TREATMENT ( after extrusion, on printable side ) only one side of LMG film is printable	DOCF002	dyn/cm	> 44

*This information is only given for general guidance and no warranty is implied.*