

PROPYPLAST SAS

B.P.11

Rue de l'Industrie

43130 RETOURNAC

FRANCE

tel: 04 71 65 20 72

fax: 04 71 65 75 31

E-mail : propyplast@propyplast.frInternet : www.propyplast.fr

USFTIML/8

**TECHNICAL DATA SHEET****LMG C 100**

Cast film PP, printable, for "In Mould Labelling" application
Color : clear

Updated : 09-23-2008

PROPERTIES	TEST METHOD	UNIT	VALUE
WEIGHT	DOCQ104	gr / m ²	90.2 +/- 5%
DENSITY	DOCQ104	gr / cm ³	0.902
YIELD	DOCQ104	in ² / lb	7,795
DYN. COEF. OF FRICTION	DOCQ109	/	0.37
YOUNG MODULUS	DOCQ109	MPa	1,250
TENSILE STRENGTH	DOCQ109	MPa	MD 37 TD 30
ELONGATION	DOCQ109	%	MD 580 TD 50
CORONA TREATMENT (after extrusion, on printable side) only one side of LMG film is printable	DOCF002	dyn/cm	> 44

Data provided above are consistent with current experience and are only provided as general information on our products. No guarantee is given of any specific attribute.