

PROPYPLAST SAS

B.P.11
 Rue de l'Industrie
 43130 RETOURNAC
 FRANCE
 tel: 04 71 65 20 72
 fax: 04 71 65 75 31
 E-mail : propyplast@propyplast.fr
 Internet : www.propyplast.fr

AFTIML/16

**TECHNICAL DATA SHEET****LMG W 12 150**

Cast film PP, printable, for "In Mould Labelling" application

Color : white

Updated : March,12 - 2009

PROPERTIES	TEST METHOD	UNIT	VALUE
WEIGHT	DOCQ104	gr/m ²	142,0 +/- 5%
DENSITY	DOCQ104	gr/cm ³	0.947
YIELD	DOCQ104	M ² /kg	7,04
DYN. COEF. OF FRICTION	DOCQ109	/	>0.35
YOUNG MODULUS	DOCQ109	MPa	1240
TENSILE STRENGTH	DOCQ109	MPa	SL 30 ST 26
ELONGATION	DOCQ109	%	SL 10 ST 10
CORONA TREATMENT (after extrusion, on printable side) only one side of LMG film is printable	DOCF002	dyn/cm	> 44

This information is only given for general guidance only and no warranty is implied.