

PROPYPLAST SAS

B.P.11
 Rue de l'Industrie
 43130 RETOURNAC
 FRANCE
 tel: 04 71 65 20 72
 fax: 04 71 65 75 31
 E-mail : propyplast@propyplast.fr
 Internet : www.propyplast.fr

USFTIML/1

**TECHNICAL DATA SHEET****LMG C 82**

Cast film PP, printable, for "In Mould Labelling" application
 Color : clear

Updated : 09-23-2008

PROPERTIES	TEST METHOD	UNIT	VALUE
WEIGHT	DOCQ104	gr / m ²	73.9 +/- 5%
DENSITY	DOCQ104	gr / cm ³	0.902
YIELD	DOCQ104	in ² / lb	9,505
DYN. COEF. OF FRICTION	DOCQ109	/	0.36
YOUNG MODULUS	DOCQ109	MPa	1,250
TENSILE STRENGTH	DOCQ109	MPa	MD 37 TD 29
ELONGATION	DOCQ109	%	MD 580 TD 50
CORONA TREATMENT (after extrusion, on printable side) only one side of LMG film is printable	DOCF002	dyn/cm	> 44

Data provided above are consistent with current experience and are only provided as general information on our products. No guarantee is given of any specific attribute.