

PROPYPLAST SAS

B.P.11
 Rue de l'Industrie
 43130 RETOURNAC
 FRANCE
 tel: 04 71 65 20 72
 fax: 04 71 65 75 31
 E-mail : propyplast@propyplast.fr
 Internet : www.propyplast.fr

AFTIML/13



**TECHNICAL DATA SHEET
 DRAFT VERSION**

LMG C IND 82



« LMG C IND » is a PP Cast film, developed for digital printing.
 This film is suitable for "In Mould Labelling" application

Color : clear

Updated : April, 27th -2009

PROPERTIES	TEST METHOD	UNIT	VALUE
WEIGHT	DOCQ104	gr/m ²	73.9 +/- 5%
DENSITY	DOCQ104	gr/cm ³	0.902
YIELD	DOCQ104	M ² /kg	13.52
DYN. COEF. OF FRICTION	DOCQ109	/	> 0.35
YOUNG MODULUS	DOCQ109	MPa	1130
TENSILE STRENGTH	DOCQ109	MPa	SL 22 ST 31
ELONGATION	DOCQ109	%	SL 220 ST 10
CORONA TREATMENT (after extrusion, on printable side) only one side of LMG film is printable	DOCF002	dyn/cm	> 44

This information is only given for general guidance and no warranty is implied.