

PROPYPLAST SAS

B.P.11
 Rue de l'Industrie
 43130 RETOURNAC
 FRANCE
 tel: 04 71 65 20 72
 fax: 04 71 65 75 31
 E-mail : propyplast@propyplast.fr
 Internet : www.propyplast.fr

AFTIML/10

**TECHNICAL DATA SHEET****LMG M 88**

LMG M is a polypropylene metallized cast film, with high gloss, for "In Mould Labelling" applications.

A special lacquer protects the metallization from scratches and acts as a print receptive surface. LMG M is suitable for offset printing (conventional and UV) with appropriate inks and varnishes.

Color : silver

Updated : march 2007

PROPERTIES	TEST METHOD	UNIT	VALUE
THICKNESS	DOCQ104	microns	88
WEIGHT	DOCQ104	gr/m ²	82.0
YIELD	DOCQ104	M ² /kg	12.5
DYN. COEF. OF FRICTION	DOCQ109	/	0.35
YOUNG MODULUS	DOCQ109	MPa	1300
TENSILE STRENGTH	DOCQ109	MPa	SL 40 ST 30
ELONGATION	DOCQ109	%	SL 580 ST 10
CORONA TREATMENT (after metallization)	DOCF002	dyn/cm	> 42

This information is only given for general guidance and no warranty is implied.

- Reels : - core : inside diameter 152 mm
 - maximum reel width : 1020 mm
 - maximum outside diameter : 800 mm
 - metallized side : outside