

PROPYPLAST S.A.S.
 BP 11
 Rue de l' Industrie
 43130 Retournac
 France
 Tel : 04 71 65 20 72
 Fax : 04 71 65 75 31
 E-mail : propyplast@propyplast.fr
www.propyplast.fr

TECHNICAL DATA SHEET

SPC IM neutre 150

« SPC IM neutre 150 » is a clear printable polypropylen cast-film for in-moulding application.

This film is UV stabilized for outdoor (garden tables or chairs, beer crates)

Updated : December,2006

PROPERTIES	TEST METHOD	UNIT	VALUE
WEIGHT	DOCQ104	gr/m ²	134.4
GLOSS (60°)	DOCQ106	%	18
SLIP (dyn. coef. of friction)	DOCQ109	/	0.38
YOUNG MODULUS	DOCQ109	MPa	620
TENSILE STRENGTH	DOCQ109	MPa	MD 19 TD 19
ELONGATION	DOCQ109	%	MD 580 TD 580
MELTING POINT	DOCQ110	°C	≅ 165
CORONA TREATMENT	DOCF002	Dyn/cm	> 38

This information is given in good faith for general guidance only and no warranty is implied