

PROPYPLAST S.A.S.  
 BP 11  
 Rue de l' Industrie  
 43130 Retournac  
 France  
 Tel : 04 71 65 20 72  
 Fax : 04 71 65 75 31  
 E-mail : [propyplast@propyplast.fr](mailto:propyplast@propyplast.fr)  
[www.propyplast.fr](http://www.propyplast.fr)

## TECHNICAL DATA SHEET

### SPC IM neutre 200

« SPC IM neutre 200 » is a clear printable polypropylen cast-film for in-moulding application.

This film is UV stabilized for outdoor ( garden tables or chairs, beer crates )

Updated : December,2006

| PROPERTIES       | TEST METHOD | UNIT              | VALUE            |
|------------------|-------------|-------------------|------------------|
| WEIGHT           | DOCQ104     | gr/m <sup>2</sup> | 179.5            |
| GLOSS ( 60° )    | DOCQ106     | %                 | 15               |
| HAZE ( % )       | DOCQ116     | %                 | 78               |
| YOUNG MODULUS    | DOCQ109     | MPa               | 650              |
| TENSILE STRENGTH | DOCQ109     | MPa               | MD 18<br>TD 17   |
| ELONGATION       | DOCQ109     | %                 | MD 580<br>TD 580 |
| MELTING POINT    | DOCQ110     | °C                | ≅ 165            |
| CORONA TREATMENT | DOCF002     | Dyn/cm            | > 38             |

*This information is given in good faith for general guidance only and no warranty is implied*