

**PROPYPLAST SAS**

B.P.11  
 Rue de l'Industrie  
 43130 RETOURNAC  
 FRANCE  
 tel: 04 71 65 20 72  
 fax: 04 71 65 75 31  
 E-mail : [propyplast@propyplast.fr](mailto:propyplast@propyplast.fr)  
 Internet : [www.propyplast.fr](http://www.propyplast.fr)

AFTA90

**TECHNICAL DATA SHEET****SPC SC W 60**

Cast film PP, printable, antistatic, for "In Mould Labelling" application.  
 SPC SC is developed for small containers.

Color : white

Updated : 11/06/08

PROPERTIES	TEST METHOD	UNIT	VALUE
WEIGHT	DOCQ104	gr/m <sup>2</sup>	Mini 53.9 Maxi 59.6
YIELD	DOCQ104	M <sup>2</sup> /kg	17.60
DYN. COEF. OF FRICTION	DOCQ109	/	0.50
YOUNG MODULUS	DOCQ109	MPa	1230
TENSILE STRENGTH	DOCQ109	MPa	SL 34.0 ST 25.0
ELONGATION	DOCQ109	%	SL 460 ST 10
CORONA TREATMENT ( after extrusion, on printable side )	DOCF002	dyn/cm	44

*This information is only given for general guidance and no warranty is implied.*