

PROPYPLAST SAS

B.P.11
 Rue de l'Industrie
 43130 RETOURNAC
 FRANCE
 tel: 04 71 65 20 72
 fax: 04 71 65 75 31
 E-mail : propyplast@propyplast.fr
 Internet : www.propyplast.fr

AFTA121

**TECHNICAL DATA SHEET****SPC SC W 65**

Cast film PP, printable, for "In Mould Labelling" application.
 SPC SC is developed for small containers.

Color : white

Updated : 01-26-2009

PROPERTIES	TEST METHOD	UNIT	VALUE
WEIGHT	DOCQ104	gr/m ²	61.5 +/- 5%
DENSITY	DOCQ104	gr/cm ³	0.947
YIELD	DOCQ104	M ² /kg	16.2
DYN. COEF. OF FRICTION	DOCQ109	/	0.50
YOUNG MODULUS	DOCQ109	MPa	1200
TENSILE STRENGTH	DOCQ109	MPa	SL 34.0 ST 25.0
ELONGATION	DOCQ109	%	SL 460 ST 10
CORONA TREATMENT (after extrusion, on printable side) Only one side of « SPC SC W » is printable	DOCF002	dyn/cm	> 44

This information is only given for general guidance and no warranty is implied.