

PROPYPLAST SAS

B.P.11
 Rue de l'Industrie
 43130 RETOURNAC
 FRANCE
 tel: 04 71 65 20 72
 fax: 04 71 65 75 31
 E-mail : propyplast@propyplast.fr
 Internet : www.propyplast.fr

FTIML/7

**TECHNICAL DATA SHEET****LMG W12 82**

Cast film PP, printable, antistatic, for "In Mould Labelling" application

Color : white

Updated : march 2008

PROPERTIES	TEST METHOD	UNIT	VALUE
WEIGHT	DOCQ104	gr/m ²	77,6
YIELD	DOCQ104	M ² /kg	12,88
DYN. COEF. OF FRICTION	DOCQ109	/	0.42
YOUNG MODULUS	DOCQ109	MPa	1250
TENSILE STRENGTH	DOCQ109	MPa	SL 35 ST 17
ELONGATION	DOCQ109	%	SL 540 ST 30
CORONA TREATMENT (after extrusion, on printable side) only one side of LMG film is printable	DOCF002	dyn/cm	> 44

This information is only given for general guidance and no warranty is implied.