



PROPYPLAST S.A.S.
BP 11
Rue de l' Industrie
43130 Retournac
France
Tel : 04 71 65 20 72
Fax : 04 71 65 75 31
E-mail : propyplast@propyplast.fr
www.propyplast.fr

TECHNICAL DATA SHEET**SPC IM blanc 130**

« SPC IM blanc 130 » is a white printable polypropylen cast-film for in-moulding application.

This film is UV stabilized for outdoor (garden tables or chairs, beer crates)

Updated : Feb,10 - 2010

PROPERTIES	TEST METHOD	UNIT	VALUE
WEIGHT	DOCQ104	gr/m ²	125.0 (+/- 5%)
GLOSS (60°)	DOCQ106	%	11
SLIP (dyn. coef. of friction)	DOCQ109	/	0.44
YOUNG MODULUS	DOCQ109	MPa	690
TENSILE STRENGTH	DOCQ109	MPa	MD 24 TD 21
ELONGATION	DOCQ109	%	MD 570 TD 580
MELTING POINT	DOCQ110	°C	≅ 165
CORONA TREATMENT	DOCF002	Dyn/cm	> 38

This information is given in good faith for general guidance only and no warranty is implied