

PROPYPLAST SAS

B.P.11

Rue de l'Industrie

43130 RETOURNAC

FRANCE

tel: 04 71 65 20 72

fax: 04 71 65 75 31

E-mail : propyplast@propyplast.frInternet : www.propyplast.fr

AFTIML/26

**TECHNICAL DATA SHEET****LMG® C SUPER CLEAR 82**

« LMG® C SUPER CLEAR 82 » is a high clarity polypropylene cast-film, printable in all conventional film printing processes (flexography, screen printing, offset UV and conventional).

This film is suitable for In-Mould Labelling applications in association with high clarity containers.

Updated : June - 2011

PROPERTIES	TEST METHOD	UNIT	VALUE
WEIGHT	DOCQ104	gr/m ²	73.9 +/- 5%
DENSITY	DOCQ104	gr/cm ³	0.902
YIELD	DOCQ104	M ² /kg	13.52
DYN. COEF. OF FRICTION	DOCQ109	/	< 0.35
CLARITY	DOCF069	%	> 95
YOUNG MODULUS	DOCQ109	MPa	1130
TENSILE STRENGTH	DOCQ109	MPa	MD 25 TD 21
ELONGATION	DOCQ109	%	MD 460 TD 470
CORONA TREATMENT (after extrusion, on printable side) only one side of « LMG® C SUPER CLEAR 82 » is printable	DOCF002	dyn/cm	> 44

STORAGE : store in a clean, controlled temperature and humidity environment.

Recommended ranges : temperature : 20 – 26°C relative humidity : 40 – 60% R.H.

Storage temperature should be the same as print room temperature.

This information is only given for general guidance and no warranty is implied.