

PROPYPLAST SAS

B.P.11
 Rue de l'Industrie
 43130 RETOURNAC
 FRANCE
 tel: 04 71 65 20 72
 fax: 04 71 65 75 31
 E-mail : propyplast@propyplast.fr
 Internet : www.propyplast.fr

AFTIML/27



**PRELIMINARY
 TECHNICAL DATA SHEET**

SPC MSD 70

“SPC MSD” is a multilayer cast-film PP, printable in all conventional film printing processes for In-Mould Labelling applications.
 This film presents a high stiffness and a low melting point.
 Printable side : smooth and semi-gloss
 Colour : white / Thickness = 70 µm.

Updated : April 2011

PROPERTIES	TEST METHOD	UNIT	VALUE
WEIGHT	DOCQ104	gr/m ²	67.7 +/- 5%
DENSITY	DOCQ104	gr/cm ³	0.968
GLOSS (60°) printable side	DOCQ106	%	45
DYN. COEF. OF FRICTION	DOCQ109	/	0.40
YOUNG MODULUS	DOCQ109	MPa	1370
TENSILE STRENGTH	DOCQ109	MPa	SL 34 ST 34
ELONGATION	DOCQ109	%	SL 10 ST 10
CORONA TREATMENT (after extrusion, on printable side) only one side of SPC MSD film is printable	DOCF002	dyn/cm	> 44

This information is only given for general guidance and no warranty is implied.